

DensDeck® Prime

Product Description:

An exceptional fire barrier, thermal barrier, cover board and recovery board used in various roofing systems. The facer is enhanced to allow adhesives to be applied more uniformly and consistently. DensDeck® Prime creates a stronger and more economical installation by reducing the amounts of adhesive used and potentially eliminates any primers. DensDeck® Prime is highly resistant to the growth of mold when tested, as manufactured, per ASTM D3273.

Packaging:

DensDeck® Prime is available in standard thicknesses of 1/4", 1/2", and 5/8" x 4' x 4' and 4' x 8' panels.

Features:

- UL code ratings available for high slopes and wood decks
- FM Approved
- Improves resistance to foot traffic and hail damage
- Excellent wind uplift ratings
- Resistant to deterioration, warping, and jobsite Damage
- Covered component under the IB Total Systems Warranty

Application:


DensDeck® Prime can be installed over approved substrates in cold adhesive roof assemblies. Refer to IB Specifications and Construction Details for additional installation instructions.

Moisture Management:

DensDeck® Prime Roof Boards, like other components used in roofing systems, must be protected from exposure to moisture before, during and after installation. Remove the plastic packaging from all DensDeck® Prime Roof Board immediately upon receipt of delivery. Failure to remove the plastic packaging may result in entrapment of condensation or moisture.

Approvals:

- ASTM C1177
- Florida Product Approval
- Miami-Dade County, Product Control Approved
- UL 790 Classification
- UL 1256 Classification
- FM Standard 4450 – 1/4" DensDeck® Prime
- 5/8" thickness—Meets requirements of Type X per ASTM C1177 and may be used in P series designs as a thermal barrier.



Typical Physical Properties*			
Property	1/4"	1/2"	5/8"
Thickness, nominal	1/4"	1/2"	5/8"
Pieces per unit for 4'x8' sheet	42	30	30
Weight, nominal, lb. / sq. ft.	1.2	2.0	2.5
¹ R-value	.28	.56	.67
Surfacing	Fiberglass Mat	Fiberglass Mat	Fiberglass Mat
² Flexural Strength, parallel, lbf, min.	≥40	≥80	≥100
³ Flute Spanability	2-5/8"	5"	8"
⁴ Permeance, perms	>30	>23	>17
Linear Variation with Change in Temp. in/in °F	8.5 x 10 ⁻⁶	8.5 x 10 ⁻⁶	8.5 x 10 ⁻⁶
Linear Variation with Change in Moisture	6.25 x 10 ⁻⁶	6.25 x 10 ⁻⁶	6.25 x 10 ⁻⁶
⁵ Water Absorption, %, max	<10	<10	<10
⁶ Compressive Strength, psi, nominal	900	900	900
Surface Water Absorption, grams, nominal	<2.0	<2.0	<2.0
⁷ Flame Spread	0	0	0
⁷ Smoke Development	0	0	0
Bending Radius	5'	8'	12'

1. Tested in accordance with ASTM C518 (heat flow meter).
 2. Tested in accordance with ASTM C473 method B.
 3. Tested in accordance with ASTM E661.
 4. Tested in accordance with ASTM E96 (dry cup method).
 5. Tested in accordance with ASTM C1177.
 6. Tested in accordance with ASTM C473.
 7. Numerical ratings are not intended to reflect performance under actual fire conditions. Flame spread index of ≤ 75 and smoke development.
 * Physical properties shown are based on data obtained under controlled conditions and are subject to normal manufacturing tolerances.

DENSDECK is a registered trademark owned by or licensed to Georgia-Pacific Gypsum LLC.