Technical Data Sheet

Styrofoam™ Deckmate™ Plus Tapered FA

IB Roof Systems®

Product Description:

An extruded polystyrene foam featuring smooth, highdensity skins and a closed cellular structure. Designed with a positive slope for drainage, it has a higher compressive strength than other commonly used foam plastic insulations in order to provide additional membrane support for conventional low-slope roof applications. Designed for fully adhered roofing systems, Styrofoam™ Deckmate™ Plus FA Tapered boasts excellent insulating characteristics, low water absorption, and excellent compressive strength.

Size/Packaging:

 Available in 2' x 8' panels with standard slopes of 1/8" per foot or 1/4" per foot.

Features:

- · Specially designed smooth, high-density skins
- · Hydrochlorofluorocarbon (HCFC) free with zero ozone depletion potential
- · Excellent insulating characteristics
- · Hydrophobic nature of polystyrene provides high resistance to both water and water vapor
- Excellent freeze-thaw resistance
- Excellent compressive strength
- Long-term durability
- Reusable in many applications
- · Covered component under the IB Total Systems Warranty

Application:

The XPS rigid insulation boards can be installed over approved substrates, directly on structural steel decks or beneath an approved cover board or thermal barrier. Note: Requires use of approved cover board or non-polystyrene insulation board as top layer; or use of approved separation sheet between the IB membrane and polystyrene insulation. Refer to IB Specifications and Construction Details for additional installation instructions.

- Meets or exceeds the requirements of ASTM C578 Standard Specification for Rigid, Cellular Polystyrene Thermal Insulation.
- · UL Standard 790 (ASTM E108) Roofing Systems Classification for various recover applications.
- FM Standard 4450

Limitations/Precautions:

When stored outdoors, keep insulation boards covered with white plastic film or light-colored tarps to protect from weather and weighted down to prevent boards from being blown around by the wind. Store above standing water. Do not leave Styrofoam™ Deckmate™ Plus FA Tapered exposed to direct sunlight for more than 90 days. Consult manufacturer if exposure is expected to be longer than 90 days. Caution: Use a temporary white covering over dark membranes or immediately cover with pavers or stone to prevent excessive heat exposure to the foam board.



STYROFOAM™ Brand Foam Insulation

Typical Physical Properties*		
Property	Test Method	Type IX
R-value ¹		
Resistance	ASTM C518	5.00
@75°F		
Compressive Strength, (psi,	107117101	0.5
10% deformation) ²	ASTM D1621	25
Flexural Strength (psi)	ASTM D203	50
Dimensional Stability ³	ASTM D2126	2.0
Water Vapor Permeance		
(max perm, 1")4	ASTM E96	1.1
Water Absorption (max %		
vol)	ASTM C272	0.1
Coefficient of Linear		
Thermal Expansion, in/in•°F	ASTM D696	3.5 x 10-5
Flame Spread ⁵	ASTM E84	
	(10 min.)	15
Smoke Development ⁵	ASTM E84	
·	(10 min.)	165
Surface Burning		
Characteristics for both		
foam core and finished	ASTM E84	
product	(10 min.)	
Flame Spread ⁴	, ,	25
Smoke Developed ⁴		<450

R means resistance to heat flow. The higher the R-value, the greater the insulating power ²Vertical compressive strength is measured at 10 percent deformation or at yield, whichever occurs

³These numerical flame spread, and smoke developed ratings are not intended to reflect hazards presented by this or any other material under actual fire conditions

5Tested at 158°F/97% RH/7 days

*Physical properties shown are based on data provided by resin manufacturers, independent test agencies and insulation manufacturers

Styrofoam™, Deckmate™ are registered trademarks owned by affiliates of DuPont de Nemours, Inc. unless otherwise noted @ 2023 DuPont