

# IB PVC MEMBRANE

## Color Selection and Rating Guide



# Color Selection and Rating Guide

ID Number	Color	Solar Reflectance (C1549)		Thermal Emittance (C1371)		SRI Value (E1980)	
		Initial	3-Year Aged	Initial	3-Year Aged	Initial	3-Year Aged
0640-0001	White	Initial	3-Year Aged	Initial	3-Year Aged	Initial	3-Year Aged
		0.87	0.74	0.88	0.89	109	91



50 Mil.	60 Mil.	80 Mil.
●	●	●

\*Available in Fleeceback and ChemGuard

ID Number	Color	Solar Reflectance (C1549)		Thermal Emittance (C1371)		SRI Value (E1980)	
		Initial	3-Year Aged	Initial	3-Year Aged	Initial	3-Year Aged
0640-0003	Cool Sand	Initial	3-Year Aged	Initial	3-Year Aged	Initial	3-Year Aged
		0.77	0.65	0.87	0.85	95	78



50 Mil.	60 Mil.	80 Mil.
	●	

ID Number	Color	Solar Reflectance (C1549)		Thermal Emittance (C1371)		SRI Value (E1980)	
		Initial	3-Year Aged	Initial	3-Year Aged	Initial	3-Year Aged
0640-0005	Cool Stone	Initial	3-Year Aged	Initial	3-Year Aged	Initial	3-Year Aged
		0.77	0.62	0.88	0.90	95	75




50 Mil.	60 Mil.	80 Mil.
	●	

ID Number	Color	Solar Reflectance (C1549)		Thermal Emittance (C1371)		SRI Value (E1980)	
		Initial	3-Year Aged	Initial	3-Year Aged	Initial	3-Year Aged
0640-0010	Tan	Initial	3-Year Aged	Initial	3-Year Aged	Initial	3-Year Aged
		0.36	0.31	0.88	0.88	39	32



50 Mil.	60 Mil.	80 Mil.
●	●	●



50 Mil.	60 Mil.	80 Mil.
	●	●



50 Mil.	60 Mil.	80 Mil.
●	●	●



50 Mil.	60 Mil.	80 Mil.
	●	



MEMBRANE FOR ROOFING SYSTEMS AS TO EXTERNAL FIRE EXPOSURE  
SEE UL DIRECTORY OF PRODUCTS CERTIFIED FOR CANADA



Order Samples!