



IB ACRYLIC HT is a premium performance, plasticizer free, single component, waterbased, 100% acrylic, elastomeric coating that is designed to help reduce surface temperatures thereby minimizing thermal expansion and contraction while providing exceptional resistance to UV degradation and long lasting and preventative solutions for the renewal and maintenance of many roof types. meets or exceeds ASTMD-6083.

PACKAGING

5 gallon Pail, 55 Gallon Drum, & 275 Gallon Tote

FEATURES AND BENEFITS

- Plasticizer free
- 55% solids by volume
- Excellent adhesion to a variety of substrates
- Special biocide formulation helps retard discoloration and dirt retention
- Unique formulation allows breathable film while providing a watertight membrane and permitting trapped moisture to escape
- Low VOC, less than 50 grams/liter
- Available in gray, tan or white

PRODUCT USE

IB Acrylic HT is a versatile, premium elastomeric coating. Designed to provide a weathering surface over metal panel roofs, smooth, and granule asphaltic roofs, concrete, and aged EPDM and aged thermoplastic single-ply membranes.

ORDERING INFORMATION

IB Acrylic HT

Item Code	Description	Size	Class
9-AHTG	IB Acrylic HT Gray	5-gal	55
9-AHTT	IB Acrylic HT Tan	5-gal	55
9-AHTW	IB Acrylic HT White	5-gal	55
9-ATHG55	IB Acrylic HT Gray	55-gal	55
9-ATHT55	IB Acrylic HT Tan	55-gal	55
9-ATHW55	IB Acrylic HT White	55-gal	55
9-ATHG275	IB Acrylic HT Gray	275-gal	55
9-ATHT275	IB Acrylic HT Tan	275-gal	55
9-ATHW275	IB Acrylic HT White	275-gal	55

COVERAGE RATE (APPROXIMATE)

Approximate coverage rate is 1.0 to 1.75 gallons per 100 square feet (16-28 wet mils) per pass depending on substrate type and roughness.

Yield (1 gal/100 sq. ft.) = 16 wet mils/8.8 dry mils.

See recommendations for specific applications. Yields will vary depending upon system selected and the smoothness and absorbency of substrate.

Solar Reflectance / Thermal Emittance / SRI Values								
Color		flectance 549)	Thermal Emittance (C1371)		SRI Value (E1980)			
White	Initial	3-Year Aged	Initial	3-Year Aged	Initial	3-Year Aged		
	0.87	0.83	0.89	0.89	110	104		

Physical Properties							
Property	Test Method	Typical Value					
% Solids by Volume	D2697	55% ± 2%					
% Solids by Weight	D1644	66% ± 2%					
Viscosity	D562	134 KU					
Elongation	D2370	600% (initial)					
		240% (aged)					
Tan alla Staan atta	D2370	500 psi (initial),					
Tensile Strength	D2370	>500 psi (aged)					
Tear Strength	D624	117 lbf/in					
Low Temperature Flexibility	D522	Pass @ -15°F (-26.1°C)					
Permeance	D1653	Perms 7					
Weight per Gallon	-	11.1 lbs./gal					
VOC Content	EPA M24	48 g/L					
Fungi Resistance	-	Zero Rating					
Water Swell	-	7.3%					
Dry Time @ 75°F (25°C)	-	90 minutes @ 50% humidity					
Recoat Window	-	6-24 hours to recoat					
Cure Time	-	30 days					
Shelf Life: (unopened container stored at temperatures between 60°F and 95°F.	-	24 months from date of manufacture.					

TEMPERATURE PRECAUTIONS

Do not apply this product below $40^{\circ}F(4.4^{\circ}C)$ or in weather conditions where the temperature will drop below $40^{\circ}F(4.4^{\circ}C)$ during the curing cycle. Upper temperature restriction (both air and substrate) for application of IB Coating products is $120^{\circ}F$ (49°C). If the substrate temperature exceeds $120^{\circ}F(49^{\circ}C)$, IB Coating products should be applied during cooler periods of the day. No coating should be applied unless surface temperature is $40^{\circ}F$ minimum and $120^{\circ}F$ maximum.

RELATIVE HUMIDITY PRECAUTIONS

Acrylic products are moisture sensitive. Do not apply this product when it is raining or if the threat of rain exists. Do not apply when the dew point is less than 5°F below the ambient temperature. Do not apply in conditions when the relative humidity exceeds 90%.

STORAGE

Always store in cool and dry location. For best results, keep product stored above 50°F (10°C) or below 90°F (32°C). Do not store in direct sunlight or in temperatures. Keep from freezing. Allow material to set at room temperature for 24 hours prior to use.

APPLICATION GUIDELINES

Application Equipment

Airless Sprayer:

- Output: Minimum 30:1 fluid to air ratio / 2.5 3.0 gal per minute
- Pressure: 3,000 to 4,000 psi
- Filter Screen: 30 mesh or larger
- Spray Gun: Contractor rated for pressure, equipped with a ballbearing swivel for ease of handling
- Hoses: 3/8" min ID up to 75 ft., 1/2" min ID up to 200 ft., and 3/4" min ID over 200 ft. Use largest diameter at pump. Hoses rated to 2X maximum pump pressure. Hose lining should be compatible with coating and required cleaning materials.
- Gun Hose: 3/8" ID x 6 feet high pressure rated with adequate WPSI.
- Extension: 12" gun extension is recommended
- Orifice Tip: .027" to .039" diameter, wide angled fan angle of 40 to 50 degrees is recommended. A reversible self-cleaning type nozzle is also recommended. Exact office size will vary with temperature of the material and ambient temperatures.
- Brush: No reduction necessary. Use synthetic filament brushes. Do not over-brush as material may start to pull.
- Roller: No reduction necessary. Use 1-1/4" nap synthetic rollers. Keep a wet edge to avoid pulling. Avoid rapid rolling which can cause bubbling.
- Spraying: When spraying material should be at least 75°F (25°C). Before applying additional coat, the previous coat must be completely dry and cured.

Mixing

No thinning or reduction is necessary. Product may separate after shipping and storage, though it may still appear mixed. When mixing is necessary, use a ³/₄ horsepower or larger electric or air operated mixer with a blade capable of uniformly mixing container. Use a 3" minimum diameter mixing blade for 5-gal pails and a minimum 6" minimum diameter blade for drums. **Never mix by hand**.

Surface Preparation

The substrate must be free of areas of ponding water, ice, snow, rain or dew, dirt, dust, grease, oil, foreign contaminants or other debris that would inhibit adhesion of coating. If such conditions exist, the roof surfaces should be properly prepared and cleaned using the specified IB cleaning solution in order to receive the new coating system.

Mildew must be removed by power washing and scrubbing with a bleach solution of 1 part bleach and 2 parts water. Repeat if necessary. Rinse thoroughly and allow to dry.

Most substrates require a bond enhancing primer and/or a compatible base coat before applying the IB Acrylic Pro Coating. Contact IBRS Technical Department at 800-426-1626 for recommendations regarding specific applications.

Application

Coating: Apply IB Acrylic HT Coating over the properly prepared substrate or compatible base coat at the rate of 1.0–1.75 gallons (3.78–6.62 L) per 100 square feet (16-28 wet mils) after the base coat has cured or at the total rate of 2.0–4.0 gallons (7.56–15.12 L) per 100 square feet (32-64 wet mils) in two to three passes of 1.0–1.5 gallons (3.78–5.67 L) per 100 square feet (16–24 wet mils) per pass. Do not exceed 1.75 gallons (6.62 L) per 100 square feet in a single pass.

Do not use as a base coat over asphaltic surfaces or EPDM membranes.

When applying in separate applications, apply at right angles to the previous coat. Coating must be evenly applied and pinhole-free. Before applying additional coat, the previous coat must be completely dry and cured. If any contamination is present on the cured surface it must be washed and completely dry before application of subsequent coats.

Adhesion Test: Adhesion of the IB Acrylic HT should always be checked. Apply 6" – 12" square of the coating and embed a piece of IB Fabric into the coating, leaving a minimum 2" tail of the fabric exposed. Allow 2-3 days for the coating to cure and perform a 90° pull test of the fabric tail to test adhesion of the coating to the substrate.

Limitations

- Refer to Substrate Preparation guidelines for proper preparation, cleaning and primer roof with any applicable bond enhancing primer before commencing with application of IB Acrylic Coating.
- This product cures by water evaporation only. Do not attempt to apply product when weather conditions are not conducive to drying. Refer to temperature and relative humidity precautions.
- Application of materials with power spray equipment will requiring some masking and erection of wind screens to prevent over spray occurrences and damage to surrounding structures, surfaces, vehicles, property or persons.

Clean Up

Clean up spills and spatters immediately with water. Flush all hoses, equipment, and tools with water followed by propylene glycol to prevent unit from rusting.

Disposal

Empty containers must be disposed of in an approved landfill in accordance with local, state, and federal regulations.

Caution

Avoid prolonged and repeated contact with skin. Do not take internally. Avoid eye contact as this material has adhesive properties. Refer to product Safety Data Sheet (SDS) for additional information pertaining to this product and prior to use or handling.

Disclaimer

All values given are approximate and are subject to change without notice. There is no implied or express warranty given through these values or statements, nor are there any assertions that the product purchased has been individually tested to conform to these standards. Testing is performed on a random basis by "in-house" and independent "third party" evaluation for the purpose of classification and or approval. Acceptance, purchase and selection of these products are the sole responsibility of the buyer or buyer's representative. We assume no responsibility for coverage, performance or injuries resulting from use. Liability, if any, is limited to replacement of the product only.

LIMITED PRODUCT WARRANTY

IB ROOF SYSTEMS, INC. ("IB") WARRANTS THE IB LABELED COATING PRODUCTS ("IB PRODUCT") SHALL BE FREE FROM ANY DEFECT IN MANUFACTURING FOR A PERIOD OF ONE (1) YEAR FROM DATE OF PURCHASE FROM IB. UPON IB'S RECEIPT OF WRITTEN NOTICE WITHIN THE WARRANTY PERIOD, IB WILL SHIP REPLACEMENT IB PRODUCT TO THE JOBSITE OR (AT IB'S SOLE DISCRETION) REFUND THE ORIGINAL PURCHASE PRICE, FOR ANY IB PRODUCT PROVED TO BE DEFECTIVE IN ITS MANUFACTURE. MISUSE, OR INSTALLATION OR STORAGE OR HANDLING OF IB PRODUCT IN ANY MANNER CONTRARY TO IB SPECIFICATIONS, INSTRUCTIONS OR RECOMMENDATIONS SHALL VOID THE COVERAGE PROVIDED HEREIN. THIS LIMITED PRODUCT WARRANTY IS ALSO VOID IF THE IB PRODUCT IS PAINTED, PATCHED, ALTERED OR COVERED IN ANY WAY WITH ANY OTHER PRODUCT OR MATERIAL. THIS LIMITED WARRANTY IS ALSO VOID IF THE IB PRODUCT IS PAINTED, PATCHED, ALTERED OR COVERED IN ANY WAY WITH ANY OTHER PRODUCT OR MATERIAL. THIS LIMITED WARRANTY IS ALSO VOID IF THE IB PRODUCT IS PAINTED, PATCHED, ALTERED OR COVERED IN ANY WAY WITH ANY OTHER PRODUCT OR MATERIAL. THIS LIMITED WARRANTY IS ALSO VOID IF THE IB PRODUCT IS PAINTES, PROMISES, REPRESENTATIONS AND GUARANTEES, WHETHER EXPRESS OR IMPLIED, INCLUDING BUT NOT LIMITED TO THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. THIS LIMITED PRODUCT WARRANTY IS THE EXCLUSIVE WARRANTY FROM IB AND REPRESENTS THE SOLE REMEDY AVAILABLE TO ANY OWNER OR USER OF IB THE PRODUCT HEREIN. IB MAKES NO OTHER REPRESENTATIONS, PROMISES, GUARANTEES, OR WARRANTIES OF ANY KIND OTHER THAN THAT STATED HEREIN. NO REPRESENTATIVE, EMPLOYEE, OR AGENT OF IB, OR ANY OTHER PERSON, HAS AUTHORITY TO ALTER THE TERMS OF THIS LIMITED PRODUCT WARRANTY. IB WILL NOT BE LIABLE IN ANY VEVENT FOR ANY DIRECT, CONSEQUENTIAL, PUNITIVE, SPECIAL, INCIDENTAL, OR OTHER SIMILAR DAMAGES OF ANY KIND, INCLUDING BUT NOT LIMITED TO PHYSICAL OR ECONOMIC DAMAGE TO THE ANY ELEMENTS OF ANY BULDING (INTERIOR OR EXTERIOR COMPONENTS), FOR MOLD OR OTHER BIOLOGICAL GROWTH, ODOR, DISCOLORATION, CHEMICAL REA