

IB Concrete Sealer

ro Grade Primer/Sealer for Masonry

Technical Data Sheet



IB CONCRETE SEALER is a high quality, rapid-drying, water-based primer intended for sealing concrete and masonry surfaces.

PACKAGING

5 gallon Pail, 55 Gallon Drum

FEATURES AND BENEFITS

- Easy to apply
- No mixing
- Rapid drying formulation
- Excellent resistance to dirt retention, chalking and weathering
- Low VOC
- Color is clear

PRODUCT USE

IB Concrete Sealer is a clear bond enhancing primer/seal coat for concrete and masonry surfaces.

ORDERING INFORMATION

IB Concrete Sealer

Item Code	Description	Size	Class
9-CS	IB Concrete Sealer Clear	5-gal	55
9-CS55	IB Concrete Sealer Clear	55-gal	55

COVERAGE RATE (APPROXIMATE)

Approximate coverage rate is 0.5 gallon per 100 square feet (8 wet mils) per pass depending on substrate type and roughness.

Yield (0.5 gal/100 sq. ft.) = 8 wet mils/2 dry mils.

See recommendations for specific applications. Yields will vary depending upon system selected and the smoothness and absorbency of substrate.

TEMPERATURE PRECAUTIONS

Do not apply this product below 40°F (4.4°C) or in weather conditions where the temperature will drop below 40°F (4.4°C) during the curing cycle. Upper temperature restriction (both air and substrate) for application of IB Coating products is $120^{\circ}F$ (49°C). If the substrate temperature exceeds $120^{\circ}F$ (49°C), IB Coating products should be applied during cooler periods of the day. No coating should be applied unless surface temperature is $40^{\circ}F$ minimum and $120^{\circ}F$ maximum.

RELATIVE HUMIDITY PRECAUTIONS

Acrylic products are moisture sensitive. do not apply this product when it is raining or if the threat of rain exists. do not apply when the dew point is less than 5°f below the ambient temperature. do not apply in conditions when the relative humidity exceeds 90%.

STORAGE

Always store in cool and dry location. For best results, keep product stored above $50^{\circ}F$ ($10^{\circ}C$) or below $90^{\circ}F$ ($32^{\circ}C$). Do not store in direct sunlight or in temperatures. Keep from freezing. Allow material to set at room temperature for 24 hours prior to use.

Physical Properties				
Property	Test Method	Typical Value		
% Solids by Volume	D2697	25% ± 2%		
Viscosity	-	200 ± 100 cps		
Weight per Gallon	-	8.6 lbs./gal		
VOC Content	EPA M24	100 g/L		
Dry Time @ 75°F (25°C)		2-3 hours @ 50% humidity		
Recoat Window		2-3 hours to recoat		
Cure Time		7 days		
Shelf Life: (unopened container stored at temperatures between 60°F and 95°F.		12 months from date of manufacture.		

APPLICATION GUIDELINES

Application Equipment

- Roller: Use 1-1/4" nap synthetic rollers. Keep a wet edge to avoid pulling. Avoid rapid rolling which can cause bubbling.
- Sprayer: Standard paint type sprayer is adequate. If sprayed the material should be at least 50°F

Mixing

No thinning or reduction is necessary. Do not dilute.

Surface Preparation

The substrate must be free of areas of ponding water, ice, snow, rain or dew, dirt, dust, grease, oil, foreign contaminants or other debris that would inhibit adhesion of coating. Masonry must be cured for a minimum of 30 days prior to application of IB Concrete Sealer.

If contamination conditions exist, the surfaces should be properly prepared and cleaned using the specified IB cleaning solution in order to receive the new coating system.

Mildew must be removed by power washing and scrubbing with a bleach solution of 1 part bleach and 2 parts water. Repeat if necessary. Rinse thoroughly and allow to dry.

Most substrates require a compatible primer to be applied prior to the application of the coating. Contact IBRS Technical Department at 800-426-1626 for recommendations regarding specific applications

Application

Concrete / Masonry: To properly prepared substrate apply a thin coat of IB Concrete Sealer at the rate of 0.5 gallon (1.89 L) per 100 square feet per pass. Multiple applications of thin coats may be applied to achieve desired results and can ensure proper drying before inclement weather.

Limitations

- Refer to Substrate Preparation guidelines for proper preparation, cleaning and primer roof with any applicable bond enhancing primer before commencing with application of IB Acrylic Coatings.
- This product cures by water evaporation only. Do not attempt to apply product when weather conditions are not conducive to drying. Refer to temperature and relative humidity precautions.
- Application of materials with power spray equipment will requiring some masking and erection of wind screens to prevent over spray occurrences and damage to surrounding structures, surfaces, vehicles, property or persons.



Clean Up

Clean up spills and spatters immediately with water. Flush all hoses, equipment, and tools with water followed by propylene glycol to prevent unit from rusting.

Disposal

Empty containers must be disposed of in an approved landfill in accordance with local, state, and federal regulations.

Caution

Avoid prolonged and repeated contact with skin. Do not take internally. Avoid eye contact as this material has adhesive properties. Refer to product Safety Data Sheet (SDS) for additional information pertaining to this product and prior to use or handling.

Disclaimer

All values given are approximate and are subject to change without notice. There is no implied or express warranty given through these values or statements, nor are there any assertions that the product purchased has been individually tested to conform to these standards. Testing is performed on a random basis by "in-house" and independent "third party" evaluation for the purpose of classification and or approval. Acceptance, purchase and selection of these products are the sole responsibility of the buyer or buyer's representative. We assume no responsibility for coverage, performance or injuries resulting from use. Liability, if any, is limited to replacement of the product only.

LIMITED PRODUCT WARRANTY

IB ROOF SYSTEMS, INC. ("IB") WARRANTS THE IB LABELED COATING PRODUCTS ("IB PRODUCT") SHALL BE FREE FROM ANY DEFECT IN MANUFACTURING FOR A PERIOD OF ONE (1) YEAR FROM DATE OF PURCHASE FROM IB. UPON IB'S RECEIPT OF WRITTEN NOTICE WITHIN THE WARRANTY PERIOD, IB WILL SHIP REPLACEMENT IB PRODUCT TO THE JOBSITE OR (AT IB'S SOLE DISCRETION) REFUND THE ORIGINAL PURCHASE PRICE, FOR ANY IB PRODUCT PROVED TO BE DEFECTIVE IN ITS MANUFACTURE. MISUSE, OR INSTALLATION OR STORAGE OR HANDLING OF IB PRODUCT IN ANY MANNER CONTRARY TO IB SPECIFICATIONS, INSTRUCTIONS OR RECOMMENDATIONS SHALL VOID THE COVERAGE PROVIDED HEREIN. THIS LIMITED PRODUCT WARRANTY IS ALSO VOID IF THE IB PRODUCT IS PAINTED, PATCHED, ALTERED OR COVERED IN ANY WAY WITH ANY OTHER PRODUCT OR MATERIAL. THIS LIMITED WARRANTY IS EXCLUSIVE AND REPLACES ALL OTHER WARRANTIES, PROMISES, REPRESENTATIONS AND GUARANTEES, WHETHER EXPRESS OR IMPLIED, INCLUDING BUT NOT LIMITED TO THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. THIS LIMITED PRODUCT WARRANTY IS THE EXCLUSIVE WARRANTY FROM IB AND REPRESENTS THE SOLE REMEDY AVAILABLE TO ANY OWNER OR USER OF IB THE PRODUCT HEREIN. IB MAKES NO OTHER REPRESENTATIONS, PROMISES, GUARANTEES, OR WARRANTIES OF ANY KIND OTHER THAN THAT STATED HEREIN. NO REPRESENTATIVE, EMPLOYEE, OR AGENT OF IB, OR ANY OTHER PERSON, HAS AUTHORITY TO ALTER THE TERMS OF THIS LIMITED PRODUCT WARRANTY. IB WILL NOT BE LIABLE IN ANY EVENT FOR ANY DIRECT, CONSEQUENTIAL, PUNITIVE, SPECIAL, INCIDENTAL, OR OTHER SIMILAR DAMAGES OF ANY KIND, INCLUDING BUT NOT LIMITED TO PHYSICAL OR ECONOMIC DAMAGE TO THE ANY ELEMENTS OF ANY SUCH DAMAGE TO THE ANY ELEMENTS OF FANY SUCH DAMAGE CLAIM AGAINST IB IS BASED UPON BREACH OF THIS WARRANTY, NEGLIGENCE, STRICT LIABILITY IN TORT, OR FOR ANY OTHER LEGAL THEORY OR CAUSE. THIS LIMITED PRODUCT WARRANT IB IS BASED UPON BREACH OF THIS WARRANTY, OR CLUSE. THIS LIMITED PRODUCT WARRANT IB IS BASED UPON BREACH OF THIS WARRANTY, TO EXCLUSIVE JURISDICTION OF AND VENUE IN THE COURTS OF DALLAS COUNTY, TEXAS. SO